

DATASHEET

# **Chicago Metallic™ L-profiles**




## **Chicago Metallic™ L-profiles**

- Visible sides adapted to the variety of grid widths
- Perfect colour match with ceiling grids
- Choice of different heights for installation purposes

#### **Assortment**

Product group	Component description	Length (mm)	Colour	Pcs per pack	Lm per pack	Kg per pack	Carton per pallet	Kg per pallet
L24x24	L-wall angle 24x24 mm	3050	Color-All, 04, 88, 11, 901, 001	20	61	13	60	782
CC 24 OUT	Outside corner for wall angle flange 24 mm		11, 001	50		0,4		
CC 24 IN	Inside corner for wall angle flange 24 mm		11, 001	50		0,3		

## **Product description**




- 24 mm wall angle with hemmed edges.

Profile can be used from both

**Body Material thickness**0,5 mm

### **Performance**







# Understanding the performance of Chicago Metallic™ grids and accessories



#### Reaction to fire

Reaction to fire is classified in accordance with EN 13501-1. Chicago Metallic steel grids and accessories are non-combustible.



#### Corrosion resistance

Chicago Metallic products produced from hot dip galvanised steel following the Sendzimir process comply with the corrosion classes of the product standard EN 13964 (A, B, C, D). The standard systems in class B are protected with 100 g/m² zinc evenly applied on both sides. The enhanced corrosion resistance (ECR) systems and accessories in class C or D have respectively a layer of 100 g/m² and 275 g/m² zinc evenly applied on both sides and are protected with an additional layer of 20 micron paint per side.



#### Fire resistance

A range of Chicago Metallic steel grids are tested in combination with different Rockfon tiles and are classified in accordance with European norm EN 13501-2 and/or national norms.



#### Load bearing performance

The load bearing performance (max. kg/m² load applicable to the grid system without exceeding the allowable deflection of the individual components) is tested in accordance with the EN 13964 standard. The accumulative value of the system deflection, shown on the data sheets, does not exceed the max. deflection as given in class 1 of the standard. Special project configurations deviating from the standard module sizes mentioned in the data sheets must be calculated by Rockfon technical services.



#### Colours

Chicago Metallic grids are available in various colours from the RAL and NCS systems, which are measured following the ISO 7724-2 and ISO 7724-3 standards. The actual colours may deviate slightly from the RAL and NCS references. Chicago Metallic grids are available in a variety of finishes from matt to high gloss, with a respective average of < 5, 15 and 50 units at a 60° angle. The matt finishing is measured at an angle of 85°. See the colour legend for their average values. The gloss unit is measured in accordance with EN13523 part 2.



#### Cleaning

All Chicago Metallic grids can be cleaned with water and a mild detergent in combination with a melamine foam sponge or microfiber cloth.

## Colour legend

For colour availability of individual components, please check the assortment table above

White 001 RAL 9003

White 901 RAL 9010

White 01 White 916 Matt White 11 RAL 9003

L value: 93 Gloss: 2 at both a 60° and 85° angle

Platinum 54

Alugrey 04

Galvanised 00 Galvanised 69 Matt Black 88 RAL 9004

Gloss: 4.5 at 60° angle and 11.5 at 85° angle

Brushed Alu 534

High Gloss Chrome 14 Carrara 57

High Gloss

White 001 / White 001 (8WW) RAL 9003 / RAL 9003 Black 08 / Black 08 (8BB) RAL 9005 / RAL 9005

White 001 / Black 08 (8WB) RAL 9003 / RAL 9005 Alugrey 04 / Black 08 (8GB) RAL 9006 / RAL 9005

## Rockfon Color-all®



# **Sounds Beautiful**

