


See SRL report C/23146/T01 for full details

The Laboratory Measurement of Random Incidence Sound Absorption to BS EN ISO 354:2003

Client: ROCKWOOL INTERNATIONAL A/S, ROCKFON
Test Date: 15/07/2015
Empty Room: Temperature: 19.8 °C Humidity: 79 %RH Pressure: 1009 mbar
Room with Sample: Temperature: 19.9 °C Humidity: 80 %RH Pressure: 1010 mbar
Sample Description: Rockfon® Blanka™ Activity 600x600x40mm
Mounting Method: E-200
Sample Area: 10.6 m²
Chamber Volume: 300 m³

Test 3				
Freq Hz	T1 sec	T2 sec	Absorp Coeff	Practical Absorp Coeff #
50*	5.00	3.59	0.36	
63*	5.07	3.34	0.47	n/a
80*	6.91	3.98	0.49	
100	7.70	4.05	0.53	
125	7.89	4.17	0.52	0.55
160	7.18	3.89	0.54	
200	6.92	3.15	0.79	
250	7.47	3.24	0.80	0.80
315	7.35	3.21	0.80	
400	6.57	2.89	0.88	
500	5.61	2.51	1.00	0.95
630	5.27	2.39	1.04	
800	5.61	2.57	0.96	
1000	6.02	2.52	1.05	1.00
1250	5.75	2.42	1.09	
1600	5.22	2.31	1.10	
2000	4.92	2.24	1.11	1.00
2500	4.49	2.14	1.12	
3150	3.92	1.99	1.13	
4000	3.28	1.82	1.12	1.00
5000	2.73	1.64	1.12	
6300*	2.11	1.43	1.04	
8000*	1.67	1.20	1.09	n/a
10000*	1.25	0.97	1.09	



α_w 1.00
Class A
 Calculated to EN ISO 11654:1997
NRC 1.00
 Calculated to ASTM C 423-01
 * Denotes frequencies outside the range covered by BS EN ISO 354:2003
 T1, empty room reverberation time
 T2, room reverberation time with sample

Practical absorption coefficient, BS EN ISO 11654:1997

v4.3